



CELEBRATING
40 YEARS
1982-2022



Chevaline Colourcure 2

Specification No: I-10 and I-11 Steel Coatings - Polyurethane
Date Prepared: July 2019

Project & Address:

Certified Applicator:

Building Owner:

Project Manager:

1. Statement of Intent

- (a) This checklist is to be completed by both the Equus Applicator and the Building Contractor, as a step by step record of compliance with both the Equus Specification provided for the contract, and the requirements of the Manufacturer for warranty.
- (b) A copy of this checklist must be forwarded to the nearest Regional Office of Equus Industries Ltd a Warranty and/or Manufacturers Producer Statement. A Warranty will not be issued by Equus Industries Ltd. without a copy of this Checklist being filed.
- (c) A copy of this checklist should form part of the Contract Documentation filed with the Project Manager on job completion, for issuance of Compliance.

2. Areas Treated

The areas to which coating is applied are detailed below, with reference to plans (where appropriate).

3. Sign Off

We confirm that all applicable processes listed in Section 4 have been correctly completed and that sign-off on each stage has been made by a person with the authority to do so.

For: _____ (Signature)
(Building Contractor)

Date: ____/____/____ _____ (Name)

For: _____ (Signature)
(Equus Applicator)

Date: ____/____/____ _____ (Name)

For: **Equus Industries Ltd** _____ (Signature)
(Equus Representative)

Date: ____/____/____ _____ (Name)



4. Checklist And Method Statement

No.	Process	Min. WFT	Completed On	Certified Applicator	Equus Representative
1.	Ensure all surfaces are dry and clean.				
2.	All steel will have been abrasive blast to AS 1627.4 Class 2.5 and factory primed with Protexx Zincure or approved alternative by Equus	125			
3.	Apply a spot primer of Protexx Zincure to all damaged coating and spot welds. Allow to dry overnight.				
4.	Apply a coat of Chevaline Colourcure HB Primer to all surfaces at 6 m ² per litre. Allow to dry overnight.	145			
5.	Apply a third coat of Chevaline Colourcure 2 topcoat at 8 m ² per litre. Allow to dry overnight.	125			
6.	Specification I-11 call for an extra coat of Chevaline Colourcure 2 to be applied at 8 m ² per litre (Walk on areas).	125			
7.	Installation completed and signed off.				