



CELEBRATING  
**40** YEARS  
1982-2022



# Chevaline Epistixx Rapid

Membrane finish to smooth cementitious surfaces

Specification No: I-3 CIP Rooms - Wet Processing - Epoxy

Date Prepared: July 2019

Project & Address:

---

---

Certified Applicator:

---

Building Owner:

---

Project Manager:

---

## 1. Statement of Intent

- (a) This checklist is to be completed by both the Equus Applicator and the Building Contractor, as a step by step record of compliance with both the Equus Specification provided for the contract, and the requirements of the Manufacturer for warranty.
- (b) A copy of this checklist must be forwarded to the nearest Regional Office of Equus Industries Ltd a Warranty and/or Manufacturers Producer Statement. A Warranty will not be issued by Equus Industries Ltd. without a copy of this Checklist being filed.
- (c) A copy of this checklist should form part of the Contract Documentation filed with the Project Manager on job completion, for issuance of Compliance.

## 2. Areas Treated

The areas to which coating is applied are detailed below, with reference to plans (where appropriate).

---

---

---

## 3. Sign Off

We confirm that all applicable processes listed in Section 4 have been correctly completed and that sign-off on each stage has been made by a person with the authority to do so.

For: \_\_\_\_\_ (Signature)  
(Building Contractor)

Date: \_\_\_\_ / \_\_\_\_ / \_\_\_\_ \_\_\_\_\_ (Name)

For: \_\_\_\_\_ (Signature)  
(Equus Applicator)

Date: \_\_\_\_ / \_\_\_\_ / \_\_\_\_ \_\_\_\_\_ (Name)

For: **Equus Industries Ltd** \_\_\_\_\_ (Signature)  
(Equus Representative)

Date: \_\_\_\_ / \_\_\_\_ / \_\_\_\_ \_\_\_\_\_ (Name)



#### 4. Checklist And Method Statement

No.	Process	Min. WFT	Completed On	Certified Applicator	Equus Representative
1.	Waterblast all surfaces at 3000 PSI. All release agents to be removed.				
2.	Confirm all panels free of all contaminants Scrub any release agent contamination with sugar soap and rinse clean.				
3.	Skim all concrete surfaces with a tight steel trowel plaster skim coat. Use Resene Multi-plast [FC]				
4.	Sand dry plaster smooth and rinse with clean water to remove dust.				
5.	Check all surfaces are dry and dust free.				
6.	Larger concrete patches to be filled with <b>Thermexx</b> leveling plaster - consult Equus for procedures.				
7.	Apply <b>Chevaline Epistixx Primer</b> thinned 40% with water at 10 m <sup>2</sup> per litre.	60			
8.	Next day spot trowel any remaining pinholes with <b>Chevaline Epistixx Rapid</b> made as a paste. There is a <b>zero</b> tolerance for pinholes.				
9.	Apply second coat of <b>Chevaline Epistixx Rapid</b> at 8 m <sup>2</sup> per litre. Dry overnight.	125			
10.	Apply a 3rd coat of <b>Chevaline Epistixx Rapid</b> at 8 m <sup>2</sup> per litre. Dry overnight.	125			
11.	Apply a 4th coat of <b>Chevaline Epistixx Rapid</b> at 8 m <sup>2</sup> per litre.	125			