



Chevaline Epistixx Rapid

Epoxy Floor Coatings

Specification No: I-7, I-8 Epoxy Flooring

Date Prepared: July 2019

Project & Address:

Certified Applicator:

Building Owner:

Project Manager:

1. Statement of Intent

- (a) This checklist is to be completed by both the Equus Applicator and the Building Contractor, as a step by step record of compliance with both the Equus Specification provided for the contract, and the requirements of the Manufacturer for warranty.
- (b) A copy of this checklist must be forwarded to the nearest Regional Office of Equus Industries Ltd a Warranty and/or Manufacturers Producer Statement. A Warranty will not be issued by Equus Industries Ltd. without a copy of this Checklist being filed.
- (c) A copy of this checklist should form part of the Contract Documentation filed with the Project Manager on job completion, for issuance of Compliance.

2. Areas Treated

The areas to which coating is applied are detailed below, with reference to plans (where appropriate).

3. Sign Off

We confirm that all applicable processes listed in Section 4 have been correctly completed and that sign-off on each stage has been made by a person with the authority to do so.

For: _____ (Signature)
(Building Contractor)

Date: ____ / ____ / ____ _____ (Name)

For: _____ (Signature)
(Equus Applicator)

Date: ____ / ____ / ____ _____ (Name)

For: **Equus Industries Ltd** _____ (Signature)
(Equus Representative)

Date: ____ / ____ / ____ _____ (Name)



4. Checklist And Method Statement

No.	Process	Min. WFT	Completed On	Certified Applicator	Equus Representative
1.	All concrete floor surfaces shall be diamond ground to remove all laitance and existing detritus. All surfaces must be clean with no contamination before proceeding.				
2.	Surface defects to be filled with Thermexx Plaster . Any major concrete dishing or ponding is to be discussed with Equus to work out a remedy.				
3.	All expansion joints are to be expressed through any plaster screeding.				
4.	All surfaces are primed with Chevaline Epistixx Primer at thinned 40% and at a spread rate of 10m ² per litre. Allow to dry overnight or longer in high humidity.	60			
5.	Specification I-7 requires an extra coat of either Chevaline Epistixx NS bodycoat or Chevaline Epistixx Rapid at 8 m ² per litre. Dry overnight.	125			
6.	All surfaces to have a full coat of Chevaline Epistixx Rapid at 8 m ² per litre. Dry overnight.	125			
7.	All surfaces to have a full final coat of Chevaline Epistixx Rapid at 8 m ² per litre. Dry overnight.	125			
8.	I-8 Specification is a reduced specification of two (2) coats of Chevaline Epistixx Rapid Topcoat, designed for non-critical areas.				