



CELEBRATING
40 YEARS
 1982-2022



Matacryl Pedestrian Deck System

Application of Matacryl Pedestrian Deck system to concrete surfaces

Specification No: _____

Date Prepared: September 2023

Project & Address:

Certified Applicator:

Building Contractor:

Building Owner/Property Manager:

1. Statement of Intent

- (a) This checklist is to be completed by both the Equus Applicator and the Main Contractor, as a step by step record of compliance with both the Equus Specification provided for the contract, and the requirements of the Manufacturers for Warranty
- (b) A copy of this checklist must be forwarded to the nearest Regional Office of Equus Industries Ltd. A Warranty will not be issued by Equus Industries Ltd. without a copy of this Checklist being filed.
- (a) A copy of this checklist should form part of the Contract Documentation filed with the Property Manager on job completion.

2. Areas Treated

The areas to which the **Matacryl Pedestrian Deck System** is applied are detailed below, with reference to plans (where appropriate).

3. Sign Off

We confirm that all applicable processes listed in Section 4 have been correctly completed and that sign-off on each stage has been made by a person with the authority to do so.

For: _____ (Signature)
 (Building Contractor)

Date: ____ / ____ / ____ (Name)

For: _____ (Signature)
 (Equus Applicator)

Date: ____ / ____ / ____ (Name)



4. Checklist And Method Statement

* Denotes those processes which must be signed off by the Building Contractor as well.

No.	Process	Completed On	Building Contractor	Equus Contractor	Notes
1.*	All concrete surfaces shall be prepared with suitable methods to achieve a clean and porous surface. Check corresponding Specification for further instructions.				
2.	Surface imperfections shall be patched, using Ready Rep Mortar .				
3.	Shrinkage cracks in the concrete surface, which are 1 mm wide or greater, shall be ground out to a minimum 6 mm-wide by 12 mm deep. Pour Matacryl Manual LM into the crack, after the Matacryl 108 H Primer has been applied.				
4.	All hairline cracks and untreated cracks up to 1mm wide shall be stripe coated with a 150mm Matacryl Manual or Thix applied at a spreading rate of 1kg per m ² . Embed 80mm wide Equus Joint Tape . After the Matacryl 108 H Primer has been applied.				
5.	Apply to concrete surfaces the suitably-catalysed Matacryl 108 H Primer to achieve a spreading rate of 0.3 - 0.5 kg per m ² , depending on surface porosity, to obtain a continuous resin film. Broadcast Walton Park aggregate into the wet layer at 0.3 – 0.4 kg per m ² . Allow to cure for 45 – 60 minutes, depending on site conditions and % of Catalyst added.				
6.	Apply to metal or plastic surfaces the suitably-catalysed Matacryl 107 CM Primer to achieve a spreading rate of 0.2 kg per m ² to obtain a continuous resin film. Allow to cure for 45 – 60 minutes, depending on site conditions and % of Catalyst added.				
7.	Apply suitably catalysed Matacryl Thix membrane at a rate of 2kg per m ² to coving turn-downs and upstands. Allow to cure for 45 – 60 minutes, depending on site conditions and % of Catalyst added.				
8.	Apply suitably-catalysed Matacryl Manual to achieve a spreading rate of 2 kg per m ² . Apply this coat by notched trowel or squeegee and then spike roll. Allow to cure for 45 – 60 minutes, depending on site conditions and % of Catalyst added.				

4. Checklist And Method Statement

* Denotes those processes which must be signed off by the Building Contractor as well.

No.	Process	Completed On	Building Contractor	Equus Contractor	Notes
9.	(Painted Finish) Topcoat: Apply over turning and high-traffic areas a coat of Matacryl STC to achieve a spreading rate of 0.2 kg per m ² . Allow to cure for 45 – 60 minutes, depending on site conditions and percentage of Catalyst added.				
10.	(Painted Finish) Topcoat: For a non-slip finish, broadcast Walton Park 18/36 aggregate into the wet resin at 1.5 kg per m ² to excess. Allow 45 – 60 minutes to cure, depending on site conditions and % of Catalyst added.				
11.	(Painted Finish) Topcoat: Apply a second coat of Matacryl STC to achieve a spreading rate of 0.3 kg per m ² . Allow to cure for 45 – 60 minutes, depending on site conditions and percentage of Catalyst added.				
12.	(Decorative Quartz Finish) Coving: Matacryl BFK is thoroughly mixed together with catalyst in accordance with site conditions. After the catalyst has been stirred in, then the aggregate shall be added and stirred in at a ratio of 1kg Matacryl BFK resin to 3-4 kg selected coloured quartz. Immediately after mixing, the material shall be applied and smoothed out with a coving trowel.				
13.	(Decorative Quartz Finish) Wear Layer: Mix Matacryl 215 WL with SNL Powder (1:1 ratio in weight) and catalyst as per mixing instructions. Pour onto deck, spread out to 2.5 kg/m ² and broadcast 0.7 – 1.2 mm quartz into the wet wear layer at approx. 4 kg per m ² (or to refusal) Allow to cure 45 to 60 minutes. Once this coat has cured, remove surplus aggregate by brooming/vacuum .				
14.	(Decorative Quartz Finish) Topcoat for areas with infrequent UV exposure: Apply suitably catalysed Matacryl 319 clear topcoat to achieve a spreading rate of 0.5 kg per m ² . Allow to cure for 45 – 60 minutes, depending on site conditions and % of catalyst added.				



4. Checklist And Method Statement

* Denotes those processes which must be signed off by the Building Contractor as well.

No.	Process	Completed On	Building Contractor	Equus Contractor	Notes
15.	(Decorative Quartz Finish) Topcoat for areas with infrequent UV exposure: Apply a second coat of Matacryl 319 clear topcoat to achieve a spreading rate of 0.2 kg per m ² . Allow to cure for 45 – 60 minutes, depending on site conditions and % of catalyst added.				
16.	(Decorative Quartz Finish) Topcoat for Exterior areas: Apply by roller or squeegee, one (1) coat of Matacryl 2K FG at a spreading rate of 4-5 kg/m ² . Allow to cure approximately 2-3 hours depending on site conditions				
17.	(Decorative Quartz Finish) Topcoat for exterior areas: Apply by roller or squeegee one (1) further coat of Matacryl 2K FG at 4-5 kg/m ² and allow to cure for 24 hours before placing in service.				
18.	Penetrations in the Matacryl System . Fixing holes filled with Tremco Dymonic FC (PU sealant) and bolts half screwed in, leaving the sealant to cure for at least 6 hours. After 6 hours, finish the screwing process. This will act as a gasket.				