



Traxx Flooring

Polyurethane coating system applied to concrete surfaces

Specification No: P4020

January 2025

Project & Address: _____

Certified Applicator: _____

Building Contractor: _____

Building Owner/Property Manager: _____

1. STATEMENT OF INTENT

- a) This checklist is to be completed by both the Equus Certified Applicator and the Building Contractor, as a step by step record of compliance with both the Equus Specification provided for the contract, and the requirements of the Manufacturers for Warranty.
- b) A copy of this checklist must be forwarded to the nearest Regional Office of Equus Industries Ltd. A Warranty will not be issued by Equus Industries Ltd. without a copy of this Checklist being filed.
- c) A copy of this checklist should form part of the Contract Documentation filed with the Property Manager on job completion.

2. AREAS TREATED

The areas to which the above system is applied are detailed below, with reference to plans (where appropriate).

3. SIGN OFF

We confirm that all applicable processes listed in Section 4 have been correctly completed and that sign-off on each stage has been made by a person with the authority to do so.

For: _____ (Building Contractor) _____ (Signature)

Date: _____ (dd/mm/yyyy) _____ (Name)

For: _____ (Equus Certified Applicator) _____ (Signature)

Date: _____ (dd/mm/yyyy) _____ (Name)

Traxx Flooring

Polyurethane coating system applied to concrete surfaces

January 2025

4. CHECKLIST AND METHOD STATEMENT

* Denotes those processes which must be signed off by the Building Contractor as well.

	Process	Completed On	Building Contractor	Equus Contractor	Notes
1.*	All concrete floor surfaces shall be acid-etched or diamond ground to remove all laitance and existing detritus. All surfaces must be clean with no contamination before proceeding.				
2.*	Surface defects to be filled with ASOCRET BIS product range. Any major concrete dishing or ponding is to be discussed with Equus to work out a remedy.				
3.*	All expansion joints are to be correctly sealed using Dymonic 100 .				
4.	Concrete surface satisfactory for installation of coating by Equus Certified Applicator.				
5.	All surfaces are primed with Chevaline Epistix Primer, mixed and diluted up to 40%, at a spread rate of 8-10m ² per litre. Allow to dry overnight.				
6.	Bodycoat : Primed surfaces receive one coat of Traxx mixed and diluted as required, at 6-8m ² per litre. Allow to dry until tack-free				
7.	Topcoat : All surfaces to receive one coat of Traxx 2KFG , at 9-10m ² per litre. Allow to dry overnight before light foot traffic, and 7 days for full curing.				
8.	System to be inspected upon completion.				