



Traxx Colourseal/Clearseal Coating

Polyurethane sealer applied to concrete surfaces

Specification No: P4091

Date Prepared: November 2024

Project & Address:

Certified Applicator:

Building Contractor:

Building Owner/Property Manager:

1. Statement of Intent

- (a) This checklist is to be completed by both the Equus Applicator and the Building Contractor, as a step by step record of compliance with both the Equus Specification provided for the contract, and the requirements of the Manufacturers for Warranty.
- (b) A copy of this checklist must be forwarded to the nearest Regional Office of Equus Industries Ltd. A Warranty will not be issued by Equus Industries Ltd. without a copy of this Checklist being filed.
- (a) A copy of this checklist should form part of the Contract Documentation filed with the Property Manager on job completion.

2. Areas Treated

The areas to which the coating applied are detailed below, with reference to plans (where appropriate).

3. Sign Off

We confirm that all applicable processes listed in Section 4 have been correctly completed and that sign-off on each stage has been made by a person with the authority to do so.

For: _____ (Signature)
(Building Contractor)

Date: ____ / ____ / ____ (Name)

For: _____ (Signature)
(Equus Applicator)

Date: ____ / ____ / ____ (Name)



4. Checklist And Method Statement

* Denotes those processes which must be signed off by the Building Contractor as well.

No.	Process	Completed On	Building Contractor	Equus Contractor	Notes
1.*	All concrete floor surfaces shall be acid-etched or diamond ground to remove all laitance and existing detritus. All surfaces must be clean with no contamination before proceeding.				
2.*	Surface defects to be filled with ASOCRET BIS product range. Any major concrete dishing or ponding is to be discussed with Equus to work out a remedy.				
3.*	All expansion joints are to be correctly sealed using Dymonic 100 .				
4.	Concrete surface satisfactory for installation of coating by Equus Certified Applicator.				
5.	IF REQUIRED: Primer Chevaline Epistix shall be mixed and diluted and applied at 10-12sqm/litre.				
6.	All surfaces shall receive a two (2) thin coats of Traxx Colourseal/Clearseal applied at a spreading rate of 10-14 sqm/litre/coat. Thin first coat up to 20% - second coat up to 10%. Allow 24 hours between coats				
7.	All surfaces shall receive a third coat of Traxx Colourseal/Clearseal applied at a spreading rate of 10-14 sqm/litre/coat. Allow 3-4 days before area is put into use.				
8.*	System to be inspected upon completion.				