

## Methodology Statement

### E-1 SPECIFICATION EXTERIOR WALL AREAS - Acrylic

July 2019

#### 1.0 PREAMBLE

This specification is for the application of a minimum three (3) coat **Chevaline Coverall / Colourglaze** System as a long-life easy-maintenance waterproof coating system on new concrete panel surfaces

#### 2.0 EQUUS COATING INSTALLATION PROCEDURES for exterior concrete panel surfaces

- Waterblast clean all surfaces at 3000psi.
- Confirm that all panels are contaminant free before proceeding.
- Plaster concrete defects and chipped concrete with Equus plaster finishes or similar approved.

***Consult Equus for accurate detailing procedures.***

- Ensure any new sealants have had a 5-day cure period before painting
- Apply a **Chevaline Coverall Primer 50/50** coat to the concrete at 8 m<sup>2</sup> per litre to all surfaces
- Apply the second coat of **Chevaline Coverall** Bodycoat at 4 m<sup>2</sup> per litre to all surfaces.
- Apply the third coat of **Chevaline Colourglaze** Topcoat at 10 m<sup>2</sup> per litre to all surfaces