

Methodology Statement

E-2 SPECIFICATION EXTERIOR WALL AREAS – Acrylic

July 2019

1.0 PREAMBLE

This specification is for the application of a minimum three (3) coat **Chevaline Coverflexx / Colourglaze** System as a long-life easy-maintenance waterproof coating system on new concrete panel surfaces.

2.0 EQUUS COATING INSTALLATION PROCEDURES for exterior concrete panel surfaces

- Waterblast clean all surfaces at 3000psi.
- Confirm that all panels are contaminant free before proceeding.
- Plaster concrete defects and chipped concrete with Equus plaster finishes or similar approved.
Consult Equus for accurate detailing procedures.
- Ensure any new sealants have had a 5-day cure period before painting.
- Apply a **Chevaline Coverall Primer 50/50** coat to the concrete at 8 m² per litre to all surfaces.
- Selective strip coat of **Chevaline Coverflexx** over all cracks by roller
- Apply the second coat of **Chevaline Coverflexx** Bodycoat at 3 m² per litre to all surfaces.
- Apply the third coat of **Chevaline Colourglaze** Topcoat at 10 m² per litre to all surfaces.