

# DANODREN H15 PLUS

## Drainage layer

June 2024

### DESCRIPTION:

DANODREN H15 PLUS is a nodular sheet composed of high density polyethylene (HDPE) and joined to a non-woven geotextile of calendered polypropylene of 115 g/m<sup>2</sup>. Nodule height is 7.3 ± 0.2 mm. It is specially designed as a drainage layer and for protection of underground walls and slabs in contact with the ground.



### PACKAGING:

SPECIFICATIONS	DANODREN H15 PLUS
Rolls	15 x 2.1 m
Nodule height	7.3 mm
Roll surface	42 m <sup>2</sup>
Rolls per pallet	6

### STANDARDS AND CERTIFICATION:

CE Marking: 2008 Certificate Number CPF: 0099/CPD/A42/0053

European standard EN 13252

The product fulfills the requirements established on the above mentioned norms, for the following applications: "F+S+R+D" Filtration, Separation, Resistance and Drainage.

### WARNING:

The information that appears in this document makes reference to the uses and utilities of Danosa's products and systems, and it is based on the knowledge that has been learnt until present, by Danosa. This is only possible if products have been stored and used in an appropriate way. Danosa is not responsible for unsuitable uses of the products or any other factors, such as meteorological facts, so Danosa is only responsible for the quality related to the provided products. Danosa reserves the right to carry out modifications without previous notice.

The values that appear in this technical sheet are the results of the tests that have been performed in our laboratory as at March 2007.

### TECHNICAL DATA:

Properties	Value	Unit	Standard
Longitudinal tensile strength	15.0, -2.0	kN/m	UNE EN ISO 10319
Transversal tensile strength	14.0, -2.0	kN/m	UNE EN ISO 10319
Longitudinal elongation at break	100, ±20	%	UNE EN ISO 10319
Transversal elongation at break	70, ±20	%	UNE EN ISO 10319
Puncture resistance (CBR)	2.5, -0.5	kN	UNE EN ISO 12236
Dynamic perforation test	16, +3	Mm	UNE EN 918
Water permeability	0.0614, -0.00921	m/s	UNE EN ISO 11058
Drainage capacity (i=0.1) in the plane of the geocomposite (at 100Kpa compression)	0.44	l/m.s	UNE EN ISP 12958
Opening size (geotextile)	160, ±30	µm	UNE EN ISO 12956
Compression resistance	180, ±20%	KN/m <sup>2</sup>	UNE EN ISO 604
Modules of elasticity	1500	N/mm <sup>2</sup>	ISO 178
Water absorption	1	Mg/4d	DIN 53495
Temperature range in use	-30 a 80	°C	-
Air volume between nodules, approx.	5.9	l/m <sup>2</sup>	-

# DANODREN H15 PLUS

## Drainage layer

June 2024

### HEALTH AND SAFETY:

For more information see relevant Safety Data Sheet (SDS).

### WARNINGS AND BANS:

Is the building product/building product line subject to warning or ban under section 26 of the Building Act 2004?	No
--	----

### MANUFACTURERS CONTACT DETAILS:

Manufacture location	Spain
Legal and trading name of manufacturer	Danosa
Manufacturer address for service	Poligono Industrial Sector 9, 19290 Fontanar, Guadalajara, Spain
Manufacturer website	<a href="http://www.danosa.com">www.danosa.com</a>
Manufacturer email	<a href="mailto:info@danosa.com">info@danosa.com</a>
Manufacturer phone number	+34 949 88 82 10