ELASTOCOL STICK H_2O

Polymer emulsion primer designed to improve the adhesion of self-adhesive waterproofing membranes

August 2026

DESCRIPTION:
ELASTOCOL STICK H_2O is a water-based polymer emulsion primer. It is designed to improve the adhesion of self-adhesive membranes on most substrates. Particularly recommended when the use of solvent-based primer is not advised.

BRANZ Appraised
Appraisal No. 819

Recommended Substrates: Concrete, wood, metal, polystyrene surfaces, gypsum boards as well as on SBS modified membranes.

APPLICATION:
****Please be aware of the restrictions below before applying ELASTOCOL STICK H_2O primer****
Surfaces must be dry, clean and free of oil, grease, debris or dirt.

1. Using a paint brush or a roller, apply ELASTOCOL STICK H_2O primer at a rate of 5 m^2/L to achieve a thickness of 8mils. Coverage may vary depending on the substrate.

2. Allow ELASTOCOL STICK H_2O to dry 1-3 hours prior to the membrane application. The drying time varies depending on the surface and on environmental factors including relative humidity, wind, ambient temperature and other factors. When the ELASTOCOL STICK H_2O primer is used on a non-porous substrate, let the primer dry completely before covering the primed surface with a waterproofing membrane.

3. The application of primer should be limited to what can be covered with waterproofing membrane in one working day. Any areas not covered with membrane during the day must be reprimed - be sure to cover all open containers when not applying primer, as the primer is volatile.

Application temperature: min. 5°C
Product temperature at the time of application: min.10°C

RESTRICTIONS:
- Membranes must be installed on the same day as the application of ELASTOCOL STICK H_2O.
- ELASTOCOL STICK H_2O must not be used over asphaltic boards (SOPRABOARD).
- ELASTOCOL STICK H_2O must not be diluted with water.

PACKAGING:

Specifications	Elastocol Stick
Physical State	Liquid
Colour	Blue
Cover rate per container	5 m^2/L
Packaging	19 L 3.78 L
Drying time	1-3 hours, must be dry to touch.

PROPERTIES:

Properties	Elastocol Stick
Specific gravity at 20°C	1.03 kg/L
Solids by weight	55%
Brookfield Viscosity 25°C	900 cP

For complete information on product installation, please consult your Equus Representative.

The information in this product data sheet is based on our experience and testing. It represents the latest information available at the time of printing, but no guarantee of its accuracy is made or implied, nor responsibility taken for use to which this information may be put. We reserve the right to alter or up-date information parameters and formulations without notice.

ELASTOCOL STICK H_2O

Polymer emulsion primer designed to improve the adhesion of self-adhesive waterproofing membranes

August 2026

STORAGE AND HANDLING:

Shelf life: ELASTOCOL STICK H_2O can be kept 24 months when properly stored in its original sealed containers.
Store in a cool and well-ventilated area. Keep away from any source of heat, freeze, humidity, oxidising agents or direct sunlight.

HEALTH AND SAFETY:

For more information, please refer to the relevant safety data sheet.

Quality, Environment and Safety Management

SOPREMA always recognises as a high level of importance, the quality of the products, the environment and safety. For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with EN ISO 9001 and EN ISO 14001.

STATEMENT OF RESPONSIBILITIY:

The technical information and application advice given in this publication is based on the present state of our best knowledge. As the information herein is of general nature, no assumption can be made as to a products suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other that those required the suitability of products for their intended use.

WARNINGS AND BANS:

Is the building product/building product line subject to warning or ban under section 26 of the Building Act 2004?	No

MANUFACTURERS CONTACT DETAILS:

Manufacture location	Canada
Legal and trading name of manufacturer	Soprema New Zealand Limited
Manufacturer address for service	Level 3, Candida Building 4, 61 Constellation Drive, Mairangi Bay, Auckland 0630, New Zealand
Manufacturer website	www.soprema.com.au
Manufacturer email	info@soprema.com.au
Manufacturer phone number	+61 3 9221 6230
Manufacturer NZBN	9429050312962

The information in this product data sheet is based on our experience and testing. It represents the latest information available at the time of printing, but no guarantee of its accuracy is made or implied, nor responsibility taken for use to which this information may be put. We reserve the right to alter or up-date information parameters and formulations without notice.