

# CHEVALINE EPISTIXX

Multi-use waterborne epoxy primer/bodycoat

April 2026

## PURPOSE AND AREAS OF USE:

A multi-use waterborne epoxy primer/bodycoat for use on most building surfaces. Generally used as an adhesion-promoting primer for Traxx flooring, or in situations where solvent release during application is not desirable. Where high-gloss and trueness of pastel colours is not important, may be used as a finish coat.

## PRODUCT:

A pigmented two-component waterborne epoxy coating based on a modified epoxy resin and polyaminoamide curing agent combination.

## PROCESS COMPATIBILITY:

Exhibits excellent adhesion to most common building materials, particularly those that are mineral-based. May be overcoated with Traxx Primers, Traxx Colourseal, Traxx Smooth/NS, Traxx SL, Chevaline Dexx, Chevaline Colourcure, Chevaline Colourcure-2, Chevaline Coverall, Chevaline Coverflexx, Equus/Tremco urethane membranes.

## COLOUR:

Standard colour is off-white. Mid and deep tone colours can be supplied as close matches on demand, subject to minimum order quantities. Pastel colours, when required are a near-match only.

## STANDARD PACK:

1, 3.5, 9 litre units. Units A & B are both packed in plastic pails.

## PHYSICAL PROPERTIES:

Liquid Material	Mixed	Unit A	Unit B
Solids (% by volume)	45	99	21
Specific Gravity	1.21	1.67	1.01
Flash Point (°C)	-	>100	-
Shelf Life	-	3 years	2 years
Appearance		Pigmented	Clear brown
Applied Coating			
Wear resistance	<55mg/1000 cycles		
Chemical resistance:			
Fresh water	Excellent		
Brine and salt	Excellent		
Fuels and greases	Excellent		
Petrol and hydrocarbon solvents	Excellent		
Caustic soda 10%	Very good		
Inorganic acids	Fair to good		
Suitable for potable water applications	Contact Manufacturer for specific advice where necessary.		

## SCOPE OF USE:

Chevaline Epistixx is generally used as a primer coat in a range of Equus flooring and waterproofing systems; Generally, the Chevaline Epistixx Rapid Floor Coating System, Traxx Floor Coating System and Chevaline Dexx Waterproofing membrane. It can be used over a variety of substrates including new or existing concrete and plywood. When installed as a primer with the correct system specification it is suitable for light-heavy duty interior floor finishes, hygiene and clean rooms, food processing, and the waterproofing of roofs and decks.

# CHEVALINE EPISTIXX

Multi-use waterborne epoxy primer/bodycoat

April 2026

## CONDITIONS OF USE:

Chevaline Epistixx must be used in accordance with the correct specifications and substrates mentioned in this TDS, or in other Equus approved technical documentation. Chevaline Epistixx must be used as a part of an approved Equus system unless otherwise specified by Equus Industries.

Not suitable for exterior conditions or in areas of with UV exposure except where specifically approved by Equus Industries.

## SURFACE PREPARATION:

Concrete plaster: Must be free of all contamination, clean and dry to touch. Surface imperfections should be filled with epoxy mortar.

Steel: Should be clean and primed with Protexx Zincure.

Old painted surfaces: Should be sanded clean and with all unsound material removed. Check compatibility with a test patch.

Stone, slate and tiles: Must be free of all contamination. Glazed tiles should be sanded to 'open' the surface.

## APPLICATION METHOD:

Units A and B for a batch must be thoroughly mixed by adding Unit A to Unit B and drill mixing for 4-5 minutes until completely homogeneous. The mixed material should then be diluted with clean water, the quantity used depending on end use.

Primer:	1.3-2.5 litres water per 3.5 litre unit
Bodycoat:	0.5-1.5 litres water per 3.5 litre unit

Note: Epistixx shall be overcoated within 24 hours of application, if there is likely to be a delay in overcoating another coat of Epistixx is required. Contact Equus Industries for more information.

## APPLICATION PROPERTIES:

### SPREADING RATE:

As primer	8-12 sqm/litre depending on surface density
As bodycoat	5-7 sqm/litre
As topcoat	7-10 sqm/litre
All rates are per litre <u>as supplied</u> . Normal d.f.t. for a 3 coat system is 160-180 microns.	

### POTLIFE:

As primer (maximum dilution)	4-6 hours
As bodycoat (minimum dilution)	1.5-2 hours

### DRY TIME (15°C, 60%RH):

Touch dry (maximum dilution)	4-6 hours
Dry to recoat (maximum dilution)	1.5-2 hours
Cure time	7-10 days for full three-coat system. <b>Note</b> that low temperatures and/or high humidities will considerably retard dry and cure times. Do not apply in temperatures below 5°C or relative humidity greater than 85%.

### THINNING / CLEANING UP:

Thin with clean tap water. Clean up gear by rinsing with water, then wiping with Xylol.

# CHEVALINE EPISTIXX

Multi-use waterborne epoxy primer/bodycoat

April 2026

**SPECIFICATION NOTES:**

Although Chevaline Epistixx is waterborne, allow adequate ventilation, not so much for safety reasons as to ensure adequate inter-coat/final drying occurs.

When used as a decorative finish externally or in areas of high UV intensity, it is recommended that Colourcure be used as the final topcoat to inhibit chalking and colour change.

**BUILDING CODE COMPLIANCE:**

For information on compliance with the New Zealand Building Code refer to the relevant Equus system TDS.

**HEALTH AND SAFETY:**

Wear barrier cream when handling Epistixx to prevent epoxy sensitisation and possible dermatitic effects. Always store above 0°C to prevent possible deterioration in the unmixed components. Do not smoke while handling the materials.

**TRANSPORT AND STORAGE:**

Unit A	No restriction
Unit B	No restriction

**WARNINGS AND BANS:**

Is the building product/building product line subject to warning or ban under section 26 of the Building Act 2004?	No
--	----

**MANUFACTURERS CONTACT DETAILS:**

Manufacture location	New Zealand
Legal and trading name of manufacturer	Equus Industries Ltd.
Manufacturer address for service	4 Sheffield Street, Blenheim 7274
Manufacturer website	www.equus.nz
Manufacturer email	info@equus.nz
Manufacturer phone number	03 578 0214
Manufacturer NZBN	9429032000306