

# MATACRYL MANUAL

## Manually applied 100% seamless waterproofing membrane

August 2024

### PRODUCT:

Matacryl Manual is a medium viscosity, urethane-modified, prereacted 100% solid membrane system based on acrylic monomers. To initiate curing, just add Matacryl Catalyst.

### USAGE:

Matacryl Manual is designed as a simple to apply, highly elastomeric liquid waterproofing membrane and coating. The cured product is a very flexible crack-bridging membrane that retains its flexibility and crack-bridging performance in service even when the temperature reaches -20°C.

The areas of application for Matacryl Manual include:

- As a Bridge Deck waterproofing membrane, on to which asphalt at temperatures up to 250°C can be directly applied.
- For sub-grade waterproofing of Buildings and Civil Engineering Structures, including below-grade Slabs.
- Waterproofing of concrete and metal Railway bridges including directly under track ballast.
- Waterproofing of Pedestrian and Vehicular trafficable areas (Balconies, Car Parks etc.)
- Protection and waterproofing of Tunnels, Channels and Dam structures.
- Waterproofing of containment structures including Reservoirs and waste and contaminated material storage structures.
- Offshore platforms.

### KEY BENEFITS:

- Highly flexible
- Excellent crack bridging characteristics
- Easy to apply
- Excellent waterproofing properties
- Very high impact and puncture resistance
- Good chemical and abrasion resistance
- Fully cured one hour after application



Matacryl Manual can be applied at a wide range of ambient and substrate temperatures (-10°C to +35°C) onto cementitious based screeds, concrete, metal, and ceramic tile substrates, and filled bitumen/asphalt under specific conditions.

### STANDARD PACKS:

30 kg units.

### PROPERTIES:

Liquid State		
Viscosity, 25°C	460-730 mPa*s	DIN 53018
Density, 25°C	1.3 g/ml	ISO 2811
Pot life/processing time at 20°C	15 min.	
Curing time at 20°C	approx. 60 min.	
Flash Point	+11.5°C	ISO 1516

Cured State tested at 20°C		
Tensile strength	8.4 N/mm <sup>2</sup>	ISO 527
Elongation	370%	ISO 527
Modulus of elasticity	78 MPa	ISO 527
Abrasion 1000 cycles	64 mg	ISO 7784-2
Dynamic crack-bridging	>5 mm	BPG
Shore A hardness	>85 IRHD	NFP 98285
Shore D hardness	55	DIN 53505

# MATACRYL MANUAL

## Manually applied 100% seamless waterproofing membrane

August 2024

### PROPERTIES continued:

Cured State samples conditioned at -20°C for 24hrs before testing		
Tensile strength	8.8 N/mm <sup>2</sup>	ISO 527
Elongation	360%	ISO 527
Modulus of elasticity	630 MPa	ISO 527
Abrasion 1000 cycles	64 mg	ISO 7784-2
Dynamic crack-bridging	>5 mm	BPG

Please note that an objective comparison with other data is only possible if norms and parameters are identical.

### SUBSTRATE PREPARATION:

The area to be waterproofed must be dry, firm, solid and free of dust, fat and oil. Laitance and loose particles must be removed thoroughly, e.g. by shot blasting. Fats or oils as well as dampness can be removed by flame blasting for example. Before application of Maticryl Manual, a suitable Maticryl Primer must be first applied, including sand-blasting when appropriate. For further details, see our general preparation and application guidelines for Maticryl waterproofing systems.

### MIXING:

Prior to use, Maticryl Manual must be carefully stirred to achieve a uniform distribution of agents contained in the product. Maticryl Manual is then thoroughly mixed together with the Maticryl Catalyst (50% dibenzoyl peroxide), in accordance with the following guidelines.

It should be noted that the amount of catalyst powder to be added depends upon the substrate temperature.

At 30°C	Add 200 grams of catalyst to a pail of 30 kg
At 20°C	Add 350 grams of catalyst to a pail of 30 kg
At 10°C	Add 700 grams of catalyst to a pail of 30 kg
At 0°C	Add 1200 grams of catalyst to a pail of 30 kg
Below -5°C	Add 1200 grams of catalyst to a pail of 30 kg and additionally add Maticryl Accelerator. Please contact your Equus Representative for further details.

**Note:** Weight to Volumetric conversion of Catalyst. 1 cc of Maticryl Catalyst weighs 0.64gm. 1gm of Maticryl Catalyst = 1.57 cc

### APPLICATION:

Maticryl Manual is designed to be manually applied using a roller or squeegee.

### CONSUMPTION:

For product consumption per m<sup>2</sup>; please consult the System Build-up Sheets.

Per layer of membrane; a minimum thickness of 1mm (=1.23kg/m<sup>2</sup>) should always be applied per coat.

### SHELF LIFE:

Six months when stored in a cool and dry place and in originally closed packaging. The optimal storage temperature is 15-20°C.

### BUILDING CODE COMPLIANCE:

For Building Code Compliance information see the (EMC) Equus Maticryl Carpark System TDS or (EMP) Equus Maticryl Pedestrian System TDS.

# MATACRYL MANUAL

Manually applied 100% seamless waterproofing membrane

August 2024

**HEALTH AND SAFETY:**

Protective clothing, gloves and safety goggles must be worn when filling, mixing or handling of Matacryl Manual. When the product is applied in enclosed areas without natural ventilation, forced ventilation must be arranged. Avoid strong concentration of vapour as well as direct contact with skin or eyes. For further information see our Safety Data Sheet.

**WARNINGS AND BANS:**

Is the building product/building product line subject to warning or ban under section 26 of the Building Act 2004?	No
--	----

**MANUFACTURERS CONTACT DETAILS:**

Manufacture location	Australia
Legal and trading name of manufacturer	Tremco CPG Pty Ltd.
Manufacturer address for service	12/4 Southridge Street, Eastern Creek, NSW 2766, Australia
Manufacturer website	
Manufacturer email	orders@tremco.com.au
Manufacturer phone number	+61 2 4648 0397