

DUO HT 4 Slates/F C180 FC MECANO

Fire-resistant waterproofing membrane for mechanical installation

July 2026

DESCRIPTION & APPLICATION:

A flexible waterproofing membrane with a dual reinforcement and a double polymeric bitumen coating. The upper coating consists of TPO (Thermoplastic Polyolefins) - modified bitumen, resulting in a high mechanical resistance and is UV resistant.

The undercoating consists of SBS (Styrene Butadiene Styrene) - modified bitumen with high elasticity and strong adhesion properties. The composite reinforcement of polyester and glass scrim, (180 g/m²) combine to provide strength and stability.

The upper side is finished with optimally pressed in coloured slates and the underside is finished with a sacrificial film.

The selvedge with a width of 13 cm is coated with SBS modified bitumen to ensure a SBS-SBS seal. This provides an easy application technique and perfectly sealed joints. With an extra wide selvedge, it is especially used as a cap sheet for single layer mechanically fixed applications.

PACKAGING:

Roll size: 8 m, Roll weight: 37 kg, Number of rolls on a pallet: 23.

TECHNICAL DATA:

Characteristics	Test Method	Units	Expression of Result	Value
Length x width	EN 1848-1	m x m	MLV ≥	8 x 1
Thickness	EN 1849-1	mm	MDV ± 5%	4
Visual defects	EN 1850-1	-	Pass/No Pass	Pass
Straightness	EN 1848-1	-	Pass/No Pass	Pass
External fire performance (1) (2) (3)	ENV 1187	-	In accordance with EN 13501-5	NPD
Reaction to fire	EN 13501-1	-	In accordance with EN 13501-1	F
Tensile strength (L/T)	EN 12311-1	N/50 mm	MDV ± 20%	880/880
Elongation (L/T)	EN 12311-1	%	MDV ± 15	50
Resistance to static loading	EN 12730	kg	MLV ≥	L25
Resistance to impact	EN 12691	mm	MLV ≤	I10
Resistance to tearing (nail shank) (LT)	EN 12310-1	N	MDV ± 50	300
Dimensional stability	EN 1107-1	%	MLV ≤	0.3
Flexibility at low temperature TPO/SBS - initial - after aging (EN 1296)	EN 1109	°C °C	MLV ≤	-15/-20 -5/-5

CodeMark


CMNZ70151



BRANZ Appraised
Appraisal No. 1169



BRANZ Appraised
Appraisal No. 685



* coloured slates

1. Upper coating in TPO-plastomer modified bitumen

2.. Composite reinforcement 180 g/m² of polyester and glass scrim

3. Under coating in SBS elastomer bitumen

** sacrificial film

DUO HT 4 Slates/F C180 FC MECANO

Fire-resistant waterproofing membrane for mechanical installation

July 2026

TECHNICAL DATA continued:

Characteristics	Test Method	Units	Expression of Result	Value
Flow resistance at elevated temperature - initial - after aging (EN 1296)	EN 1110	°C °C	MLV ≥	110 100
Joint strength: peel resistance	EN12316-1	N/50 mm	MDV ± 50	150
Joint strength: shear resistance	EN 12317-1	N/50 mm	MDV ± 250	750
Water tightness	EN 1928		Pass/No Pass	Pass
Water tightness after stretching at low temperature	EN 13897	%	MLV ≥	10
Adhesion of granules	EN 12039	%	MDV ± 5%	10

MDV: Manufacturer's Declared Value

MLV: Manufacturer's Limiting Value

NPD: No Performances Declared

SCOPE OF USE:

DUO HT 4 Slates/F C180 FC Mecano is used as a UV and weather resistant single layer cap sheet in the DUO Roof & Deck membrane system.

The product is specifically designed to be mechanically fastened as a single layer membrane. Generally used in roofing renovation projects over existing membranes or roofing.

DUO HT 4 Slates/F C180 FC Mecano can be overlaid with Fixplus or other approved pedestals, pavers and decking, Kraitec Step walkway tiles, and Soprasolar or other approved solar panel supports. Suitable for other waterproofing applications with written approval by Equus Industries Ltd.

CONDITIONS OF USE:

In areas of regular foot traffic, higher than for normal maintenance traffic, the membrane must be overlaid with pedestals and pavers or decking, Kraitec Step walkway tiles or other approved protection. The product must be installed by a Certified Equus Applicator. Verification of their status can be confirmed by a current applicator certificate or by contacting Equus Industries. Any installation must be done in accordance with the latest specifications and technical documentation, or with written approval by Equus Industries Ltd.

BUILDING CODE COMPLIANCE:

B2 Durability - B2.3.1 (b), DUO HT 4 Slates/F C180 FC Mecano has a durability of at least 15 years, when installed with the correct specification, installation, and maintenance. See CodeMark CMNZ70151, BRANZ Appraisal 685, DUO Durability Study.

E2 External moisture - E2.3.1, E2.3.2, E2.3.7 Test data, together with in-service history in New Zealand and internationally, of the correctly installed DUO HT 4 Slates/F C180 FC Mecano membrane over correctly designed and constructed substrates, show that the membrane successfully resists the ingress of moisture. See CodeMark CMNZ70151, BRANZ Appraisal 685, DUO Durability Study.

F2 Hazardous building materials - F2.3.1 Well known experience with the type of materials used together with in-service history, show that DUO HT 4 Slates/F C180 FC Mecano complies with this performance requirement. Refer to SDS at www.equus.nz



4421EB Equus Duo Roof & Deck Membrane by Soprema



BBA n 98/3537



NL-BSD-BD 007



BC2-310-0296-0123-01



DUO HT 4 Slates/F C180 FC MECANO

Fire-resistant waterproofing membrane for mechanical installation

July 2026

SUPPORTING DOCUMENTATION:

Can be found at: www.equus.nz

STORAGE:

Membrane rolls shall be stored in a dry area, always in an upright (vertical) position. Do not lay rolls flat (horizontal) when storing.

HEALTH & SAFETY:

SOPRADERE QUICK primer is solvent-based and must be used with adequate ventilation. Remove all naked flames and sources of ignition. Adequate ventilation is required to minimise exposure to bitumen fumes during the torching process. Safety Data Sheet (SDS) must be read and understood prior to use of product.

WARNINGS AND BANS:

Is the building product/building product line subject to warning or ban under section 26 of the Building Act 2004?	No
--	----

MANUFACTURERS CONTACT DETAILS:

Manufacture location	Belgium
Legal and trading name of manufacturer	Soprema New Zealand Limited
Manufacturer address for service	Level 3, Candida Building 4, 61 Constellation Drive, Mairangi Bay, Auckland 0630, New Zealand
Manufacturer website	www.soprema.com.au
Manufacturer email	info@soprema.com.au
Manufacturer phone number	+61 3 9221 6230
Manufacturer NZBN	9429050312962