

# ALSAN MASTIC 2200

## Flexible mastic

March 2024

**DESCRIPTION:**

Flexible mastic based on bitumen and synthetic rubber. Used for sealing small tears, cracks, joints and local repairs.


**TECHNICAL DATA:**

Properties	ALSAN MASTIC 2200
Composition	Bitumen and synthetic rubber
Temperature resistance	-20/+80°C
Application temperature	+5/+35°C
Consumption	15-20 m/cartridge

**PACKING AND STORAGE:**

310 ml cartridge.  
20 cartridges/box.

Minimum 12 months in original unopened packaging, stored in a dry and cool place, protected from sunlight at a temperature between +10 and +25°C.

**INSTALLATION:**

ALSAN MASTIC 2200 is applied with a gun on a clean and dust-free surface. It has excellent adhesion to most materials without prior treatment with a primer. It can be applied on a slightly damp surface.

Apply ALSAN MASTIC 2200 so that it is in full contact and has good adhesion to the edges of the joint. The curing time is 4 to 24 hours depending on the conditions and dimensions of the joint.

**CLEANING TOOLS:**

White spirit.

**HEALTH AND SAFETY:**

For more information, please refer to the relevant safety data sheet.

**QUALITY, ENVIRONMENT AND SAFETY MANAGEMENT:**

SOPREMA always recognises as a high level of importance, the quality of the products, the environment and safety. For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with EN ISO 9001 and EN ISO 14001

**WARNINGS AND BANS:**

Is the building product/building product line subject to warning or ban under section 26 of the Building Act 2004?	No
--	----



624

2 Pages

TECHNICAL  
DATA  
SHEET

Page 2 of 2

# ALSAN MASTIC 2200

Flexible mastic

March 2024

## MANUFACTURERS CONTACT DETAILS:

Manufacture location	Belgium
Legal and trading name of manufacturer	Soprema New Zealand Limited
Manufacturer address for service	Level 3, Candida Building 4, 61 Constellation Drive, Mairangi Bay, Auckland 0630, New Zealand
Manufacturer website	<a href="http://www.soprema.com.au">www.soprema.com.au</a>
Manufacturer email	<a href="mailto:info@soprema.com.au">info@soprema.com.au</a>
Manufacturer phone number	+61 3 9221 6230
Manufacturer NZBN	9429050312962